## ORIGINAL ARTICLE

# The effects of cooling conditions on surface integrity in machining of Ti6Al4V alloy

G. Rotella • O. W. Dillon Jr. • D. Umbrello • L. Settineri • I. S. Jawahir

Received: 17 July 2013 / Accepted: 4 November 2013 / Published online: 19 November 2013 © Springer-Verlag London 2013

Abstract This paper presents results from a comparative study of machining of Ti6Al4V alloy under dry, minimal quality lubrication, and cryogenic cooling conditions using coated tools at varying cutting speeds and feed rates. The influence of the cooling conditions on surface integrity and the product performance was studied in terms of surface roughness, metallurgical conditions, including microstructure, hardness, grain refinement, and phase transformation of the machined product. Results show that cooling conditions affect surface integrity of the product signifying the benefits of cryogenic cooling in improving the overall product performance.

**Keywords** Machining · Surface integrity · Cryogenic cooling · Ti6Al4V

# **1** Introduction

Global competitive market in manufacturing demands highquality products at reduced costs and improved productivity rates. Advanced technological solutions are urged for globally competitive sustainable manufacturing [1]. The aircraft industry is one of the most relevant example where all finished products must be produced with consistently high quality, to

Department of Mechanical, Energy and Management Engineering, University of Calabria, Rende, CS 87036, Italy e-mail: d.umbrello@unical.it

G. Rotella · O. W. Dillon Jr. · D. Umbrello · I. S. Jawahir Institute for Sustainable Manufacturing (ISM), University of Kentucky, Lexington, KY 40506, USA

L. Settineri

Department of Management and Production Engineering, Politecnico di Torino, Torino, TO 10129, Italy ensure high safety standards for performance over the lifetime. In the manufacture of aerospace components, surface integrity plays a key role due to its strong correlation with the functional performance and service life of such engineered components. Numerous aircraft components are produced exclusively by a range of machining operations. Their use and functional performance heavily depend on being able to design and manufacture these components with high degree of reliability and predictability of their functionality and safety. Surface characteristics of machined products such as microstructure, surface roughness, hardness, and residual stresses are among the most significant characteristics determining the reliability and the functional performance of a product [2]. A long-lasting product satisfying high-quality standards helps to save energy and costs during its functional performance, and therefore can be considered more sustainable. A sustainable product would not only require less-frequent replacement with upgradability and maintainability but also must demonstrate high reliability and improved safety during its service life [3]. Metalworking fluids (MWFs) have generally been considered highly effective, and as integral part of manufacturing processes for decades, despite conflicting studies showing the actual effectiveness of their use in several operations in terms of unfavorable product and process performance results. Over the years, the MWFs have also changed dramatically, due to high demands to provide better performance, and facilitate improved health and safety conditions. In metal machining, the use of cutting fluids is regarded as an area for potential improvement because of the serious health and environmental threat associated with their use, disposal, and related high costs. Thus, various researchers have examined the benefits, drawbacks, and conditions necessary for machining a range of materials with dedicated cooling methods such as flood-cooling, dry, and minimal quality lubrication (MQL) machining [4–8].

At the onset, it appears that the most promising idea would be to use a more sustainable and cost-effective process by

G. Rotella · D. Umbrello (🖂)

eliminating the traditional MWFs, since they are not embodied in final products. However, since MWFs are often required to produce high-performance products, their elimination is not always possible, especially when difficult-to-cut materials are machined [4].

Several conscious cooling approaches [4, 9, 10] have been widely investigated in the recent time, especially for difficultto-cut materials. In particular, liquid nitrogen (LN<sub>2</sub>) has been applied as a cryogenic coolant and, consequently, it has been widely investigated, especially for machining Ti6Al4V titanium alloy [11–15]. Most of the research demonstrated improvements in various aspects of Ti6Al4V machinability, either by cryogenically freezing the workpiece or by spraying LN<sub>2</sub> to the cutting zone. The main functions of cryogenic cooling in metal cutting were defined by Hong and Zhao [11] as effectively removing heat from the cutting zone. Hence, it has the potential to decrease the cutting temperatures [16], modify the frictional characteristics at the tool/chip interfaces [17], and change the properties of the workpiece and the tool material [18].

Other research showed the effects of different cooling strategies, including cryogenic cooling, on surface and subsurface hardness, founding that it generally increases when a drastic cooling is applied [14, 19]. Particularly, specimens of Ti6Al4V alloys machined under cryogenic cooling showed rapid increase in their strength and hardness, while their toughness and ductility showed little variation as the temperature decreases [15]. Therefore, simultaneously cooling the workpiece to enhance the chemical stability of the workpiece and cooling the cutting tool to enhance the hardness and chemical stability of the tool were recommended as an effective cryogenic strategy for titanium alloy [15].

Furthermore, it was also stated that liquid nitrogen should have some sort of positive boundary lubrication effect [17]. Strong adhesion between tool rake and chip face occurs in dry cutting conditions and lower temperatures could make the material harder and less sticky by reducing adhesion between the interacting surfaces resulting in a low friction [17]. As a consequence, the reduced friction coefficient at the tool–chip interface generates lower cutting forces than those observed in dry machining.

Finally, it has been also reported that cryogenic process successfully generates thicker surface layers consisting of ultrafine/nano-grain structures on different materials such as steels and Ni and Mg alloys [20–22]. Along with the benefits on grain refinement, cryogenic under severe plastic deformation (SPD) is also expected to introduce compressive residual stresses on the surface and subsurface layers [23].

In summary, the cryogenic processing-induced surface integrity modifications can be beneficial for a series of processes and products performance. However, very few studies have been devoted to quantify these simultaneous changes in surface integrity during cryogenic processing [23–25], whereas no complete investigation on surface integrity are done when Ti alloys are investigated, but only studies on cryogenic cooling influence on surface roughness are reported [26, 27]. Therefore, the main objective of this paper is to investigate and establish the effects of different cooling/lubricating conditions on surface integrity (surface roughness, hardness modification, phase changes, grain size, etc.) in machining of Ti6Al4V alloy at varying cutting speeds and feed rates, to enable optimized product performance.

## 2 Experimental procedure

The orthogonal cutting operation was conducted on a Mazak QuickTurn10 CNC turning center (Fig. 1), and it involved radially cutting of the Ti6Al4V (354 HV) disks at feed rates of 0.1 and 0.05 mm/rev at three cutting speeds (Table 1). The cutting tests were designed to avoid undesired effects on the machined surface related to transient conditions. At the prescribed end-of-cut, the cutting tool was instantaneously retracted at maximum feed to avoid the rubbing of the tool



Fig. 1 Experimental setup for orthogonal cutting tests with a MQL and b cryogenic cooling systems

 Table 1 Experimental test conditions

v <sub>c</sub> [m/min]	70	110	150	70	110	150
f [mm/rev]	0.05			0.10		
Cooling	Dry, cryogenic, MQL			Dry, cryogenic, MQL		

against the machined workpiece surface. The utilized cutting tool inserts are coated carbides, Kennametal<sup>®</sup> KCU10 grade, with an advanced PVD TiAlN coating, and are of triangular shape—TNGG432FS series, mounted on a MTCNN-124 tool holder (providing rake and clearance angles of 7° and 11°, respectively). The measured initial cutting edge radius, prior to machining, was consistent and was in the range of 8–10 µm in all tested tool inserts.

The effect of variations in cutting edge radius during each test was avoided by allowing fresh cutting edge for each test of short duration. The MQL tests were performed applying vegetable oil emulsion through an external nozzle to the cutting zone properly selecting a flow rate of 60 ml/h [28] (with a pressure of 4 bar), while the cryogenic coolant  $(LN_2)$  was applied through a 2-mm nozzle (with a pressure of 12 bar) to the cutting region, thus creating a surface temperature of -185 °C. After machining, all samples were metallographically processed: sectioned, mounted on a resin holder, and then polished and etched. The etchant employed is the Kroll's reagent that is recommended for etching nonferrous materials and recommended for Ti alloys. The composition of the reagent is 92 ml of distilled water, 6 ml of nitric acid, and 2 ml of hydrochloric acid. A fresh etchant was used for each sample and the immersion time was around 20 s for each sample. The microstructural changes have been analyzed using a scanning electronic microscopy (SEM). The surface and subsurface hardness values were also measured on a micro hardness indenter Future Tech F-7. The surface roughness was measured and analyzed using a Zygo7300® optical white light interferometry-based surface profilometer. Additionally, XRD patterns between 30 and 75°  $2\theta$  of the processed surfaces were also acquired for investigating the phase transformation taking place on the machined surface. The Xray diffractometer used Cu-K $\alpha$  radiation ( $\lambda = 1.54184$  Å,

on machined samples under dry, MQL, and cryogenic cooling conditions

Fig. 2 Mean surface roughness

 $K\alpha_1/K\alpha_2=0.5$ ) from a source operated at 40 kV and 40 mA. Samples were accordingly positioned at the center of plate into the X-ray goniometric in order to guarantee a correct beam radiation. The scan increment was  $0.05^{\circ}$ .

## 3 Experimental results and discussion

#### 3.1 Surface roughness

The surface roughness of each test was measured five times at different locations along the surface. The observed trend for the mean surface roughness  $R_a$  is reported in Fig. 2a for a feed rate of 0.05 mm/rev, while in Fig. 2b the results for a feed rate of 0.1 mm/rev are reported. A decreasing trend for the mean surface roughness  $R_a$  is seen, when the cutting speed increases. The feed rate seems to have a very minor influence on the roughness trend.

The  $R_a$  measurements obtained in machining with cryogenic coolant were found to be largely and consistently superior to those obtained in dry and MQL machining, and at higher cutting speed, MQL produced comparable results. The overall surface roughness for all three cooling conditions is always below 0.3 µm, which is a very good finish surface quality. It has been shown that a smooth surface with better surface roughness would prevent the initiation of cracks under cyclic loads [29].

## 3.2 Surface and subsurface hardness

Figure 3a shows the surface hardness of the samples machined at 0.05 mm/rev feed rate, while the results related to the higher feed rate are reported in Fig. 3b. The results clearly demonstrate that cryogenic cutting condition allows the material to reach a higher surface hardness in all the test conditions.

Figure 4 shows the hardness variation of machined samples at 0.1 mm/rev from the surface to the bulk material. A deeper hardness alteration is verified in all cryogenically machined samples. MQL performs better than dry machining by exhibiting a higher surface hardness and maintaining it up to a greater depth.



Fig. 3 The measured surface

for a 0.05 mm/rev and b

0.10 mm/rev feedrate





Fig. 4 Surface and subsurface hardness profiles for experimental conditions at f=0.1 mm/rev and cutting speed of **a** 70 m/min; **b** 110 m/min; and c 150 m/min

Dry cutting with its higher temperatures does not allow an increase in the surface and subsurface hardness, and cryogenic machining with its lower temperatures promotes the hardness increase during the cutting process. In fact, a combination of reduced thermal softening effect and greater grain refinement results in a higher surface hardness in the machined samples.

On the other hand, dry machining, due to the lack of coolant, tends to create softer and rougher surfaces. Hardness induced by the use of MQL during machining lies between the dry and the cryogenic cooling since the mix of lubricant and pressurized air slightly reduces the temperature during cutting. However, the MQL cooling effect, including the rate and intensity, is not comparable with that developed during cryogenic machining due to its significantly reduced thermal gradient and capacity.

#### 3.3 Microstructure

The grain size and shape, and the grain boundary arrangements in Ti alloys have a significant influence on the induced mechanical properties of the machined component. The ability to manipulate the phase/grains present, by alloying, is responsible for achieving desirable properties in Ti and its alloys [30]. It is generally known that the microstructure influences the behavior of the Ti alloys, and a refined grain structure is more desirable from the point of view of tensile yield stress in metallic materials. In contrast, the ultimate tensile stress of Ti alloys is not significantly influenced by grain size, but its ductility, as represented by elongation or reduction in area, and it generally is improved with smaller grain size [30]. Also, fatigue life can strongly depend on this parameter [31-33]. Thus, the grain size was measured on each machined surface as well as on the as received material using both an optical and SEM microscope.

The microstructure of the as-received Ti6Al4V used in this study is shown in Fig. 5; the dark region is the  $\alpha$  phase and the light region is the  $\beta$  phase. The  $\alpha$  grains were measured to be around 20 µm.

Generally, higher  $\alpha$  content results in higher creep resistance and high-temperature strength, while higher  $\beta$  content leads to higher density and room temperature strength [30].



Fig. 5 SEM micrograph of an etched microstructure of the as-received Ti6Al4V with *dark region* for HCP  $\alpha$  phase and *light region* for BCC  $\beta$  phase

However, the combination of softer  $\alpha$  grains and harder  $\beta$  phase is usually preferred for achieving good performance in an alloy for the strength and the fatigue life [30].

Figure 6 shows the SEM microstructures of the machined samples at  $v_c$ =150 m/min and f=0.05 mm/rev. These results show that both the bulk material and the machined surface present an equiaxed microstructure of primary  $\alpha$  grains and intergranular beta ( $\beta$ ) grains. Also, the structure near the machined surface presents a more dense  $\beta$  phase leading to higher room temperature strength [30].

All the examined samples present a refinement of the mean grain diameter from the bulk to the surface although the grain refinement is more evident for MQL and cryogenic conditions, where the microstructures are more dense and present a deeper SPD layer. Figure 7 highlights how the lubricant/ coolant and the processing parameter affect the microstructure of the machined samples showing the grain refinement evolution from the less influencing condition (70 m/min, 0.05 mm/rev, dry cutting) to the most effecting condition (150 m/min, 0.10 mm/rev, cutting under cryogenic cooling).

It is worth to point out that the process parameters influence a lot the microstructural changes under dry conditions while the cooling effect of cryogenic prevails on the microstructural behavior. This trend is better shown in Fig. 8 where the grain size on the machined surface for all the experimental tests are reported. Obtaining smaller grains when using cryogenic cooling conditions is related to the fact that this cooling process prevents grain growth after the dynamic recrystallization (DRX), which in turn is the result of the severe plastic deformation process [34]. These results also confirm the potential of the use of cryogenic cooling to generate a stronger machined product, with a harder surface, and less prone to crack initiation [31, 32, 34].

#### 3.4 Phase changes-XRD analysis

Phase change is a microstructural feature that cannot be optically detected, but it strongly influences the material properties. For example, transformed  $\beta$  phase products in Ti alloys can affect tensile strengths, ductility, toughness, and cyclic properties [30]. Processing of Ti6Al4V alloy can lead to formation of two secondary phases: Ti3Al and  $\omega$  on the surface. Ti3Al is detrimental to the resistance to stress corrosion of the material, while the  $\omega$  phase is undesirable due to its brittleness [30]. First of all, it is important to underline that Xray diffraction of all the investigated samples does not show any peak corresponding to Ti3Al or  $\omega$  phase formation.

Figure 9 shows the XRD patterns for some of the investigated cutting conditions in which the  $\alpha$  and  $\beta$  phases were identified according to Bragg's law and data reported in the materials handbook [35]. The results generally show that the  $\beta$  transus temperature was never reached during the process since the  $\alpha$  phase does not significantly decrease in peak intensity [36]. However, the  $\beta$  peak changes with the process



Fig. 6 SEM images of the machined samples under a dry; b MQL; and c cryogenic conditions at  $v_c = 150$  m/min and f = 0.05 mm/rev. ( $\alpha$ —dark grains;  $\beta$ —light grains)





Fig. 8 Comparison of measured grain size variation at varying the cutting speed: a 0.05 mm/rev; b 0.10 mm/rev





conditions and the lubricant/coolant used. In particular, it increases under dry condition and slightly increases with the cutting speed. In contrast, the feed rate does not significantly affect the  $\beta$  peak.

Another cardinal aspect to be highlighted from the XRD analysis is related to the relative intensity and the width, which are influenced from cutting process and cooling condition. According to Herbert et al. [37], different intensity represents different grain size. As it is clearly seen in Fig. 7, primary  $\alpha$ grains refinements are observed when higher cutting speeds and cryogenic cooling are utilized. The XRD profiles, in terms of intensity and width of the  $\alpha$  peak (Fig. 9), are in accordance with the grain size trends reported in Fig. 9.

Also, the ratio of the two phases influences the behavior of Ti alloys, and therefore it is crucial to identify these differences in the processed material [38]. In fact, the  $\alpha$  phase partially transforms to the  $\beta$  phase at temperatures above  $\alpha / (\alpha + \beta)$  transus [38]. Thus, the volume fraction of  $\alpha$  and  $\beta$  phases was calculated from the XRD results as follows [39]:

$$\frac{I_{\beta}}{I_{\alpha}} = A \frac{f_{\beta}}{f_{\alpha}} \tag{1}$$

where I is the peak intensity of the interested phase and f its volume fraction, and A is the ratio between the relative integrated intensities of both phases [39]. According to each XRD spectrum, the  $\beta$  percentage increases from the 11 % in the unprocessed material to the 30 % in the machined surface in dry machining at 150 m/min and 0.1 mm/rev. The peak ratios show a similar trend between cryogenic and MOL coolants, which exhibit a slightly lower  $\beta$  percentage than dry machining (about 22 % for cryogenic and 25 % for MQL). In contrast, the feed rate slightly affects the volume fraction variation, while the  $\beta$  percentage decreases when increasing the cutting speed. The  $\beta$  phase is not materially so different from the  $\alpha + \beta$  phase even if, an increase of the  $\beta$  phase on the surface can increase the efficiency of the material since the formation of a little  $\beta$ permits the alloy to be strengthened [30]. However, a reduction of grain size is more effective than a decrease of primary  $\alpha$  volume fraction for improving the fatigue life in both the low cycle fatigue and high cycle fatigue ranges [30]. The effectiveness of strengthening in Ti alloys appears to be more influenced by the number and fineness of phase boundaries and the grain size [30].



Fig. 9 XRD results obtained for machined samples at a  $v_c$ =70 m/min and f=0.05 mm/rev; b  $v_c$ = 150 m/min and f=0.05 mm/rev; c  $v_c$ =150 m/min and f=0.10 mm/rev

Experimental observations reported in this paper show the capability of cryogenic cooling to improve the product surface integrity in machining of Ti6Al4V alloys. In particular, the surface roughness strongly benefits from the use of cryogenic cooling as well as the hardness at the surface and subsurface level. Furthermore, the surface microstructural changes highlight how cryogenic coolant improves the DRX mechanism containing the regrowth phase. Thus, cryogenically machined samples generally show a superior surface finishing (combination of mean surface roughness, microhardness, and grain size), which is partially reached by MQL machined specimens only under certain conditions. In contrast, dry machining permits to achieve a higher  $\beta$  volume fraction, which is beneficial for increased material strength at room temperature.

From a sustainability perspective, cryogenic machining is more environmentally friendly when compared with the traditional flood cooling methods and MQL machining. It also contributes to make products having better surface integrity and quality by generating smaller grains.

Overall, this study demonstrates that the different cooling/ lubrication methods affect the surface characteristics of Ti6Al4V alloy. In particular, cryogenic cooling can significantly improve the product surface characteristics having a great impact on its quality and potentially improve its reliability.

Acknowledgments The authors gratefully acknowledge the help provided by Tao Lu and Charles Arvin during the experimental work conducted at the Institute for Sustainable Manufacturing, University of Kentucky, and Mr. J. Backus from Kentucky Geological Survey for his help with the XRD measurements. The authors should also like to acknowledge Mr. Steve Chen of Kennametal Tools for the donation of cutting tools.

## References

- Jovane F, Yoshikawa H, Alting L, Boer CR, Westkamper E, Williams D, Tseng M, Seliger G, Paci AM (2008) The incoming global technological and industrial revolution towards competitive sustainable manufacturing. CIRP Ann Manuf Technol 57(2):641–659
- Jawahir IS, Brinksmeier E, M'Saoubi R, Aspinwall DK, Outeiro JC, Meyer D, Umbrello D, Jayal AD (2011) Surface integrity in material removal processes: recent advances. CIRP Ann Manuf Technol 60(2):603–626
- Jayal AD, Badurdeen F, Dillon OW Jr, Jawahir IS (2010) Sustainable manufacturing: modeling and optimization challenges at the product, process and system levels. CIRP J Manuf Sci Technol 2(3):144–152
- Shokrani A, Dhokia V, Newman ST (2012) Environmentally conscious machining of difficult-to-machine materials with regard to cutting fluids. Int J Mach Tools Manuf 57:83–101
- Klocke F, Eisenblatter G (1997) Dry cutting. CIRP Ann Manuf Technol 46(2):519–526
- Jayal AJ, Balaji AK (2009) Effects of cutting fluid application on tool wear in machining: interactions with tool-coatings and tool surface features. Wear 267(9):1723–1730

- Weinert K, Inasaki I, Sutherland JW, Wakabayashi T (2004) Dry machining and minimum quantity lubrication. CIRP Ann Manuf Technol 53(2):511–537
- Marksberry PK, Jawahir IS (2008) A comprehensive tool-wear/toollife performance model in the evaluation of NDM (near dry machining) for sustainable manufacturing. Int J Mach Tools Manuf 48:878– 886
- Ulatan D, Ozel T (2011) Machining induced surface integrity in titanium and nickel alloys: a review. Int J Mach Tools Manuf 51: 250–280
- Ezugwu EO (2005) Key improvements in the machining of difficultto-cut aerospace superalloys. Int J Mach Tools Manuf 45:1353–1367
- Hong SY, Zhao Z (1999) Thermal aspects, material considerations and cooling strategies in cryogenic machining. Clean Prod Process 1(2):107–116
- Hong SY, Ding Y (2001) Micro-temperature manipulation in cryogenic machining of low carbon steel. J Mater Process Technol 116(1): 22–30
- Hong SY, Broomer M (2000) Economical and ecological cryogenic machining of AISI 304 austenitic stainless steel. Clean Prod Process 2(3):157–166
- Hong SY, Ding Y, Ekkens RG (1999) Improving low carbon steel chip breakability by cryogenic chip cooling. Int J Mach Tools Manuf 39:1065–1085
- O'Sullivan D, Cotterell M (2001) Temperature measurement in single point turning. J Mater Process Technol 118:301–308
- Hong SY, Ding Y (2001) Cooling approaches and cutting temperatures in cryogenic machining of Ti-6Al-4V. Int J Mach Tools Manuf 41:417–1437
- Hong SY, Ding Y, Jeong J (2002) Experimental evaluation of friction and liquid nitrogen lubrication effect in cryogenic machining. Mach Sci Technol 6(2):235–250
- Yildiz Y, Nalbant M (2008) A review of cryogenic cooling in machining processes. Int J Mach Tools Manuf 48:947–964
- Ezugwu EO, Bonney J, Da Silva RB, Cakir O (2007) Surface integrity of finished turned Ti–6Al–4V alloy with PCD tools. Int J Mach Tools Manuf 47:884–891
- Zurecki Z, Ghosh R, Frey JH (2003) Investigation of white layer formed in conventional and cryogenic hard turning of steels, in: Proc. ASME Int. Mechanical Engineering Congress and Exposition (IMECE 2003), Washington, DC, USA, November 2003, ASME Pub., pp. 16–21.
- Pusavec F, Hamdi H, Kopac J, Jawahir IS (2011) Surface integrity in cryogenic machining of nickel based alloy-inconel 718. J Mater Process Technol 211(4):773–783
- 22. Pu Z, Outeiro JC, Batista AC, Dillon OW Jr, Puleo DA, Jawahir IS (2012) Enhanced surface integrity of AZ31B Mg alloy by cryogenic machining towards improved functional performance of machined components. Int J Mach Tools Manuf 56:17–27
- 23. Jawahir IS, Pu Z, Yang S, Rotella G, Kaynak Y, Lu T, Deshpande A, Umbrello D, Dillon Jr. OW (2012) Cryogenic processing of materials for enhanced product life, performance and sustainability. In: 15th Int. Conf. on Advances in Materials & Processing Technologies (AMPT 2012) Keynote paper (in press).
- 24. Dhar NR, Paul S, Chattopadhyay AB (2002) Machining of AISI 4140 steel under cryogenic cooling—tool wear, surface roughness and dimensional deviation. J Mater Process Technol 123(3):483–489
- Umbrello D, Micari F, Jawahir IS (2012) The effects of cryogenic cooling on surface integrity in hard machining: a comparison with dry machining. CIRP Ann Manuf Technol 61(1):103–106
- Wang ZY, Rajurkar KP (2000) Cryogenic machining of hard-to-cut materials. Wear 239:168–175
- Dhananchezian M, Pradeep Kumar M (2011) Cryogenic turning of the Ti–6Al–4V alloy with modified cutting tool inserts. Cryogenics 51:34–40

- Sadeghi MH, Haddad MJ, Tawakoli T, Emami M (2009) Minimal quantity lubrication-MQL in grinding of Ti–6Al–4V titanium alloy. Int J Adv Manuf Technol 44:487–500
- McClung RC (2007) A literature survey on the stability and significance of residual stresses during fatigue. Fatigue Fract Eng Mater Struct 30:73–205
- Donachie Jr. MJ (2000) Titanium: a technical guide. ASM International, Materials Park, OH, 44073–000.
- Chan KS (2003) A microstructure-based fatigue-crack-initiation model. Metall Mater Trans 34:43–58
- Chan KS (2009) Changes in fatigue life mechanism due to soft grains and hard particles. Int J Fatigue 32:526–534
- Chan KS (2010) Roles of microstructure in fatigue crack initiation. Int J Fatigue 32:1428–1447
- 34. Rotella G, Lu T, Settineri L, Dillon OW Jr, Jawahir IS (2012) Dry and cryogenic machining: comparison from the sustainability

perspective. In: Seliger G (ed) Sustainable manufacturing. Springer, Berlin, pp 95–100

- JCPDS (2010) International Centre for Diffraction Data, Powder Diffraction File, Inorganic Phases, Sets 1–60, 2010.
- 36. Zeng L, Bieler TR (2005) Effects of working, heat treatment, and aging on microstructural evolution and crystallographic texture of α, α', α" and β phases in Ti–6Al–4V wire. Mater Sci Eng A 392:403–414
- Herbert C, Axinte D, Hardy M, Brown PD (2012) Investigation into the characteristics on the white layers produced in a nickel-based superalloy from drilling operations. Mach Sci Technol 16(1):40–52
- Fan Y, Cheng P, Yao YL (2005) Effect of phase transformations on laser forming of Ti–6Al–4V alloy. J Appl Phys 98:013518–013519
- Pederson R, Babushkin O, Skystedt F, Warren R (2003) Use of high temperature X-ray diffractometry to study phase transitions and thermal expansion properties in Ti-6Al-4V. Mater Sci Technol 19(11): 1533–1538